



Makes all
**MORTAR and
RENDER** mixes
more workable,
stickier, fluffier,
stronger and
harder



**Safer, Easier &
More Economical**

**HYDRATED LIME
ALTERNATIVE***

mix it with the best.

Call **1300 CEMENT** (1300 236 368) or visit cementaustralia.com.au
for more information about our range of products



EcoSYN™

Hydrated Lime Alternative



- ✓ Hydrated Lime and additive alternative in cement/lime/sand mortars*
- ✓ Non-hazardous by NOHSC Criteria - Safe for Users
- ✓ Ideal for DIY and commercial projects
- ✓ Mortar produced with EcoSYN™ conforms to AS 3700 Masonry Structures

SUGGESTED MIX RATIOS

APPLICATION	PROPORTIONS BY VOLUME		
	Cement	Sand	EcoSYN™
Bricklaying M3 Mortar	1	5	100-300g per 20kg Cement
Bricklaying M4 Mortar	1	4	100-300g per 20kg Cement

**Please note: EcoSYN™ cannot be used as an alternative for Hydrated Lime in soil stabilisation and septic waste applications.*

LIMITATIONS: EcoSYN™ is not a Hydrated Lime alternative in traditional sand/lime mortars.

SUGGESTIONS FOR USE

Charge the mixer with water. Add 50% of the sand to the mixer followed by cement, EcoSYN™ and the remaining sand.

Allow all ingredients to mix for a minimum of 8 minutes.

Add water as required to achieve ideal workability (do not use excess water).

Depending on quality of sand, dose rates of EcoSYN™ can vary for bricklaying mortar (approx. 100g-150g). EcoSYN can be increased up to 300g or decreased to 100g and will not harm the mortar in any way.

When rendering, start with 220g of EcoSYN™ and increase up to 300g if more stickiness is required.

Mix it with the best.

Call **1300 CEMENT** (1300 236 368) or visit cementaustralia.com.au for more information about our range of products

